

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
13 January 2005 (13.01.2005)


PCT

(10) International Publication Number
WO 2005/004254 A2

- (51) International Patent Classification⁷: H01M
- (21) International Application Number: PCT/JP2004/007585
- (22) International Filing Date: 26 May 2004 (26.05.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2003-192170 4 July 2003 (04.07.2003) JP
- (71) Applicant (for all designated States except US): MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD. [JP/JP]; 1006, Oaza-Kadoma, Kadoma-shi, Osaka 5718501 (JP).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): MURAKAMI, Hajime.
- (74) Agents: ISHII, Kazuo et al.; Kitahama-Yamamoto Building, 3-6, Kitahama 2-chome, Chuo-ku, Osaka-shi, Osaka 5410041 (JP).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,

[Continued on next page]

(54) Title: A POSITIVE ELECTRODE CURRENT COLLECTOR FOR A MANGANESE DRY BATTERY AND A MANGANESE DRY BATTERY USING THE SAME



(57) Abstract: To provide a positive electrode current collector for a manganese dry battery including a carbon rod with a low density yet with good retention of the sealing property of the battery during high temperature storage. The positive electrode current collector for a manganese dry battery comprises a carbon rod and paraffin wax containing a hydrocarbon compound having a molecular weight of 300 to 500 impregnated in the carbon rod, the paraffin wax containing a hydrocarbon compound having a molecular weight of not greater than 310 in an amount of not greater than 0.5 wt%.

WO 2005/004254 A2

BEST AVAILABLE COPY

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
13 January 2005 (13.01.2005)

PCT

(10) International Publication Number
WO 2005/004254 A2

(51) International Patent Classification⁷:

H01M

(21) International Application Number:

PCT/JP2004/007585

(22) International Filing Date: 26 May 2004 (26.05.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

2003-192170

4 July 2003 (04.07.2003) JP

(71) Applicant (for all designated States except US): MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD.
[JP/JP]; 1006, Oaza-Kadoma, Kadoma-shi, Osaka
5718501 (JP).

(72) Inventor; and

(75) Inventor/Applicant (for US only): MURAKAMI, Hajime.


(74) Agents: ISHII, Kazuo et al.; Kitahama-Yamamoto Building, 3-6, kitahama 2-chome, Chuo-ku, Osaka-shi, Osaka 5410041 (JP).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,

[Continued on next page]

(54) Title: A POSITIVE ELECTRODE CURRENT COLLECTOR FOR A MANGANESE DRY BATTERY AND A MANGANESE DRY BATTERY USING THE SAME



(57) Abstract: To provide a positive electrode current collector for a manganese dry battery including a carbon rod with a low density yet with good retention of the sealing property of the battery during high temperature storage. The positive electrode current collector for a manganese dry battery comprises a carbon rod and paraffin wax containing a hydrocarbon compound having a molecular weight of 300 to 500 impregnated in the carbon rod, the paraffin wax containing a hydrocarbon compound having a molecular weight of not greater than 310 in an amount of not greater than 0.5 wt%.



SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *without international search report and to be republished upon receipt of that report*

DESCRIPTION

A POSITIVE ELECTRODE CURRENT COLLECTOR FOR A MANGANESE DRY BATTERY AND A MANGANESE DRY BATTERY USING THE SAME

Technical Field

The present invention relates to a positive electrode current collector for a manganese dry battery comprising a carbon rod, and a manganese dry battery using the same.

Background Art

A carbon rod having been used for a positive electrode current collector of a manganese dry battery is porous. In order to prevent air from entering the battery through the pores, the carbon rod is usually impregnated with wax.

Conventionally, 135°F paraffin wax has been used as wax with a low melting point. This paraffin wax usually contains several percent of a component that melts at 45°C or lower. Since manganese dry batteries might be exposed to a temperature of 45°C or higher during transportation or storage, storage tests are usually performed at 45°C. The storage tests include: durability test during high temperature storage, and accelerated evaluation in which durability during long-term storage at room temperature is evaluated in a shortened

period of time. For this reason, the use of paraffin wax containing a component that melts at 45°C is not preferred. Carbon rods having been used have a high density and thus only a small amount of paraffin wax is required for the impregnation, so that there is little effect on the sealing property of the battery due to the melting of the paraffin wax as long as carbon rods with a high density are used.

However, in the case of using a carbon rod with a low density as the carbon rod for a manganese dry battery with the aim of rationalization such as cost reduction, the carbon rod with a low density have a high porosity and thus a large amount of paraffin wax to be impregnated is required. Therefore, a large amount of paraffin wax will be melt during storage at 45°C and problems arise such as melting of a sealant resulting from the melted paraffin wax and sealing failure of the battery resulting from the melting of a sealant.

One possible way to solve the above problems is to use paraffin wax with a high melting point. Japanese Laid-Open Patent Publication No. Hei 3-297063, for example, proposes a method for preventing the component of an impregnating agent containing paraffin wax from seeping out during high temperature storage by setting the melting point of the impregnating agent to 90°C or higher.

Among paraffin wax with a high melting point, some of the paraffin wax contains a component that melts at 45°C or lower depending on production areas of the raw material and

production methods, so that the sealing property of the battery might be reduced during high temperature storage even when paraffin wax with a high melting point is used.

Disclosure of Invention

Thus, in order to solve the above problems, an object of the present invention is to provide a positive electrode current collector for a manganese dry battery including a carbon rod with a low density yet with good retention of the sealing property of the battery during high temperature storage. Another object of the present invention is to provide a manganese dry battery having high temperature storage characteristics by using the above positive electrode current collector.

In order to solve the above problems, the positive electrode current collector for a manganese dry battery of the present invention comprises a carbon rod and paraffin wax containing a hydrocarbon compound having a molecular weight of 300 to 500 impregnated in the carbon rod, wherein the amount of a hydrocarbon compound having a molecular weight of not greater than 310 in the paraffin wax is not greater than 0.5 wt%.

The amount of the hydrocarbon compound having a molecular weight of not greater than 310 in the paraffin is preferably measured by gas chromatography.

The carbon rod preferably has a density of 1.50 to

1.75 g/cm³.

Polybutene is preferably applied as a sealant in the manganese dry battery.

The manganese dry battery of the present invention preferably comprises the aforesaid positive electrode current collector.

More preferably, the manganese dry battery of the present invention further comprises a sealing member having an aperture for fitting the positive electrode current collector therein, and polybutene is placed as a sealant in the fitting portion between the positive electrode current collector and the sealing member.

While the novel features of the invention are set forth particularly in the appended claims, the invention, both as to organization and content, will be better understood and appreciated, along with other objects and features thereof, from the following detailed description taken in conjunction with the drawings.

Brief Description of Drawings

FIG. 1 is a front view, partly in cross section, of a manganese dry battery in accordance with the present invention.

Best Mode for Carrying Out the Invention

The positive electrode current collector for a

manganese dry battery of the present invention comprises a carbon rod impregnated with paraffin wax, which contains a hydrocarbon compound having a molecular weight of 300 to 500. Further, the amount of the hydrocarbon compound having a molecular weight of not greater than 310 in the paraffin wax is not greater than 0.5 wt%.

The main feature of the present invention lies in the use of specific paraffin wax as the wax to be impregnated in the carbon rod as described above, so that even a battery comprising a carbon rod with a low density can retain the sealing property thereof.

The paraffin wax that can be used in the present invention is required to contain 0 to 0.5 wt% of a hydrocarbon compound having a molecular weight of not greater than 310, which is a component that melts at 45°C, in consideration of the battery to be produced being stored at 45°C during the evaluation of battery characteristics.

This is because, if the amount of the hydrocarbon compound having a molecular weight of not greater than 310 exceeds 0.5 wt%, the amount of the paraffin wax melted from the carbon rod at 45°C or lower will be increased, likely to cause the melting of the sealant.

An example of the method for determining the amount of the hydrocarbon compound having a molecular weight of not greater than 310 that melts at 45°C or lower in the paraffin wax is gas chromatography.

The carbon rod used in the present invention preferably has a density of 1.50 to 1.75 g/cm³, more preferably a low density of 1.50 to 1.65 g/cm³. Even a carbon rod with such low density can minimize the melting of the paraffin wax and the reduction of sealing property if the carbon rod is impregnated with the paraffin wax described above.

The carbon rod may be prepared by a conventional method, or it may be a commercially available carbon rod. The carbon rod can be prepared, for example, by extruding a mixture of graphite and a binder such as pitch in a rod. The impregnation of the carbon rod with the paraffin wax may be done by a conventional method.

By impregnating the carbon rod with the paraffin wax as described above, it is possible to produce a positive electrode current collector of the present invention.

Moreover, with the use of the positive electrode current collector, a manganese dry battery with excellent sealing property can be produced by a conventional method.

In the manganese dry battery, a sealing member having an aperture for fitting the positive electrode therein is provided in order to seal the battery, and polybutene is placed in the fitting portion between the positive electrode current collector and the sealing member.

By using the positive electrode current collector of the present invention to produce a manganese dry battery, it

is possible to minimize the melting of the paraffin wax itself even when the battery is stored at a high temperature. In particular, when polybutene is used as the sealant for the dry battery, it is possible to prevent the paraffin wax and polybutene from melting and mixing with each other.

In the following, examples of the present invention are described in detail, but it is to be understood that the present invention is not limited to them.

EXAMPLE 1

A low-quality carbon rod with a low density of 1.62 g/cm³ was prepared by extruding a mixture of graphite and pitch as a binder in a rod. The carbon rod was impregnated with paraffin wax containing a hydrocarbon compound with a melting point listed in Table 1 and a molecular weight of not greater than 310 in an amount listed in Table 1 to give a positive electrode current collector 2 of the present invention.

Table 1

	Density of carbon rod (g/cm ³)	Paraffin wax		Amount of HC* (wt%)
		Melting point (°F)	Amount in carbon rod	
Comp. Ex. 1	1.71	135	5.0	1.5
Comp. Ex. 2	1.62	135	8.5	1.5
Comp. Ex. 3	1.62	145	8.4	0.8
Ex. 1	1.62	145	8.5	0.5
Ex. 2	1.62	145	8.6	0.0
Ex. 3	1.62	155	8.7	0.0
Ex. 4	1.71	145	5.1	0.0

* HC = hydrocarbon compound having a molecular weight of not greater than 310

The amount of the hydrocarbon compound having a molecular weight of not greater than 310 and a melting point of not higher than 45°C in the paraffin wax was determined by gas chromatography. The gas chromatography analysis was performed under the conditions shown in Table 2 using GC17A available from Shimadzu Corporation as an analyzer.

Table 2

Item		Contents
Analytical method		Gas chromatography
Equipment		GC17A from Shimadzu Corp..
Column		Ultra ALLOY-1 from Frontier Lab Ltd. (30 mm × 0.25 mm i.d. df=0.25 μm)
Temperature conditions	Column oven	50°C → heated (heating rate 15°C/min) → 350°C (maintained for 30 min.)
	Vaporizing chamber	350°C
	Detector	380°C
Flow conditions	Carrier gas	He
	Control mode	Split
	Column inlet pressure	100 kPa
	Column flow rate	1.27 ml/min
	Column linear velocity	29.5 cm/s
	Total volume	30 ml
	Split ratio	1:20
	Type	FID
Detector	ATTEN	3

With the use of the positive electrode current collector 2, an R 20 type manganese dry battery was produced by the following process.

FIG. 1 shows a front view, partly in cross section, of an R 20 type manganese dry battery produced in this example.

A cylindrical positive electrode material mixture 1 was housed in a negative electrode zinc can 4, which was obtained by forming metallic zinc into a bottomed cylindrical case, with a separator 3 interposed therebetween. Inside the positive electrode material mixture 1 was inserted the positive electrode current collector 2 produced above. The positive electrode material mixture 1 and the negative electrode zinc can 4 were isolated by the separator 3. The positive electrode material mixture 1 was prepared by mixing manganese dioxide, conductive carbon black and an electrolyte at a weight ratio of 50:10:40. The electrolyte was made of zinc chloride and water at a weight ratio of 3:7.

A sealing member 5 was formed of polyolefin resin and had an aperture 5a for fitting the positive electrode current collector 2 in the center thereof. When the positive electrode current collector 2 was fitted into the aperture 5a of the sealing member 5, polybutene serving as the sealant was placed in the fitting portion between the sealing member 5 and the positive electrode current collector 2. A Kraft paper 9, that is, a disc-shaped paper with a hole in the center thereof obtained by punching, was placed on the top of the positive electrode material mixture 1. The upper portion of the positive electrode current collector 2 running through the sealing member 5 and the center hole of the Kraft paper 9 was

brought into contact with a positive electrode terminal 11 in order for the positive electrode current collector 2 to serve as the current collector for the positive electrode.

The positive electrode terminal 11 made of tinplate comprised a cap-shaped central portion for covering the top of the positive electrode current collector 2 and a flat peripheral portion. An insulating ring 12 made of resin was provided on the edge of the flat peripheral portion of the positive electrode terminal 11. A bottom paper 13 to ensure insulation was placed between the bottom of the positive electrode material mixture 1 and the negative electrode zinc can 4. A sealing ring 7 was placed on the edge of the flat peripheral portion of a negative electrode terminal 6.

A resin tube 8 made of a heat-shrinkable resin film to ensure insulation was provided to entirely cover the negative electrode zinc can 4. The upper portion of the resin tube 8 covered the edge of the sealing member 5 and the lower portion thereof covered the bottom surface of the sealing ring 7.

The resin tube 8 was then completely covered with a cylindrical metal outer jacket 10 made of tinplate. The upper and lower portions of the cylindrical metal outer jacket were respectively bent inward. The tip of the upper portion of the jacket was brought into contact with the insulating ring 12 by the bending. Thereby, the insulating ring 12, the flat peripheral portion of the positive electrode terminal 11, the

upper portion of the resin tube 8, the periphery of the sealing member 5 and the opening edge of the negative electrode zinc can 4, as well as the lower portion of the resin tube 8, the sealing ring 7 and the negative electrode terminal 6, were respectively fixed to a certain position.

[Evaluation]

There were produced 100 manganese dry batteries as described above. Immediately after the production, each of the batteries was checked for voltage. After 3 months storage at 45°C, each battery was again checked for voltage. Subsequently, the average of the voltage difference (voltage drop) between the voltage immediately after the production and that after the storage at 45°C was determined.

There were also produced another 10 manganese dry batteries as described earlier. Each of the batteries was continuously discharged with a load of 2.2 Ω . After 3 months storage at 45°C, each battery was again discharged in the same manner. The discharge was performed in an atmosphere of 20°C.

EXAMPLES 2 to 4 and COMPARATIVE EXAMPLES 1 to 3

An R 20 type manganese dry battery for each example was produced in the same manner as in EXAMPLE 1 except that the combination of paraffin wax and a carbon rod with a density shown in Table 1 was used. A positive electrode current collector and a manganese dry battery obtained here were respectively evaluated in the same manner as in EXAMPLE 1.

The paraffin wax used in each example contained a hydrocarbon compound having a melting point shown in Table 1 and a molecular weight of not greater than 310 in an amount shown in the same table.

Table 3 shows the evaluation results of the batteries of EXAMPLES 1 to 4 and COMPARATIVE EXAMPLES 1 to 3.

Table 3

	Voltage drop (mV)	Time for continuous discharge at 2.2 Ω (min.)	
		Before storage	After storage (remaining ratio)
Comp. Ex. 1	5	583	551 (95)
Comp. Ex. 2	11	580	528 (91)
Comp. Ex. 3	7	583	542 (93)
Ex. 1	5	580	551 (95)
Ex. 2	3	581	566 (97)
Ex. 3	3	580	562 (97)
Ex. 4	3	578	560 (97)

This table indicates that the batteries of EXAMPLES 1 to 4 having paraffin wax containing a hydrocarbon compound with a molecular weight of not greater than 310 in an amount of 0.5 wt% or lower exhibited better high temperature storage characteristics than those of COMPARATIVE EXAMPLES 1 to 3.

In the batteries of COMPARATIVE EXAMPLES 2 and 3, the amount of the component melted out during the high temperature storage increased. This is because a carbon rod with a low density was used in the examples so that each of the batteries was required to have increased amount of paraffin wax contained and thus the amount of the component

that melts at 45°C or lower in the paraffin wax exceeded 0.5 wt%. The sealant composed mainly of polybutene melted and compatibly blended with the melted paraffin wax, which deteriorated its sealing effect. Presumably, these above factors made it easier for air to enter the battery through the pores of the carbon rod, leading to the degradation of the battery.

In the batteries of EXAMPLES 1 to 3, a carbon rod with a low density was also used so that they also contained an increased amount of the paraffin wax. However, the amount of the component that melts at 45°C or lower in the paraffin wax was not greater than 0.5 wt%. As a result, the amount of the component melted out during the storage at 45°C was small, and thus the sealing property of the battery was able to be effectively retained. In other words, the present invention was able to minimize the melting of the paraffin wax and to prevent the paraffin wax and polybutene from melting and compatibly blending with each other in the case of using polybutene as the sealant of the dry battery. Thereby, the sealing effect of the sealant was able to be retained.

As described above, according to the present invention, it is possible to provide a positive electrode current collector for a manganese dry battery having a carbon rod with a low density yet with good retention of the sealing property of the battery during high temperature storage. It is also possible to provide a manganese dry battery with

excellent high temperature storage characteristics by using the positive electrode current collector.

Although the present invention has been described in terms of the presently preferred embodiments, it is to be understood that such disclosure is not to be interpreted as limiting. Various alterations and modifications will no doubt become apparent to those skilled in the art to which the present invention pertains, after having read the above disclosure. Accordingly, it is intended that the appended claims be interpreted as covering all alterations and modifications as fall within the true spirit and scope of the invention.

Industrial Applicability

By using the positive electrode current collector of the present invention to produce a manganese dry battery, it is possible to minimize the melting of the paraffin wax itself even when the battery is stored at a high temperature. In particular, when polybutene is used as the sealant for the dry battery, it is possible to prevent the paraffin wax and polybutene from melting and mixing with each other.

CLAIMS

1. A positive electrode current collector for a manganese dry battery comprising: a carbon rod, and paraffin wax containing a hydrocarbon compound having a molecular weight of 300 to 500 impregnated in said carbon rod,

said paraffin wax containing a hydrocarbon compound having a molecular weight of not greater than 310 in an amount of not greater than 0.5 wt%.


2. The positive electrode current collector for a manganese dry battery in accordance with claim 1, wherein the amount of said hydrocarbon compound having a molecular weight of not greater than 310 in said paraffin wax is measured by gas chromatography.

3. The positive electrode current collector for a manganese dry battery in accordance with claim 1, wherein said carbon rod has a density of 1.50 to 1.75 g/cm³.

4. A manganese dry battery comprising the positive electrode current collector for a manganese dry battery in accordance with any one of claims 1 to 3.

5. The manganese dry battery in accordance with claim 4, further comprising: a sealing member having an aperture for fitting said positive electrode current collector, and polybutene placed as a sealant in the fitting portion between said positive electrode current collector and said sealing member.

FIG. 1



(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
13 January 2005 (13.01.2005)


PCT

(10) International Publication Number
WO 2005/004254 A3

- (51) International Patent Classification⁷: **H01M 4/62**, 4/75, 6/06
- (21) International Application Number: **PCT/JP2004/007585**
- (22) International Filing Date: **26 May 2004 (26.05.2004)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
2003-192170 **4 July 2003 (04.07.2003)** **JP**
- (71) Applicant (for all designated States except US): **MAT-SUSHITA ELECTRIC INDUSTRIAL CO., LTD.** [JP/JP]; 1006, Oaza-Kadoma, Kadoma-shi, Osaka 5718501 (JP).
- (72) Inventor; and
(75) Inventor/Applicant (for US only): **MURAKAMI, Hajime.**
- (74) Agents: **ISHII, Kazuo et al.**; Kitahama-Yamamoto Building, 3-6, Kitahama 2-chome, Chuo-ku, Osaka-shi, Osaka 5410041 (JP).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): **AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.**
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): **ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,**

[Continued on next page]

(54) Title: **A POSITIVE ELECTRODE CURRENT COLLECTOR FOR A MANGANESE DRY BATTERY AND A MANGANESE DRY BATTERY USING THE SAME**



(57) Abstract: To provide a positive electrode current collector for a manganese dry battery including a carbon rod with a low density yet with good retention of the sealing property of the battery during high temperature storage. The positive electrode current collector for a manganese dry battery comprises a carbon rod and paraffin wax containing a hydrocarbon compound having a molecular weight of 300 to 500 impregnated in the carbon rod, the paraffin wax containing a hydrocarbon compound having a molecular weight of not greater than 310 in an amount of not greater than 0.5 wt%.

WO 2005/004254 A3



ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(88) Date of publication of the international search report:
14 April 2005

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP2004/007585

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H01M4/62 H01M4/75 H01M6/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 03/083962 A (INOKUCHI KOJI ; OGINO KEIJI (JP); MURAKAMI HAJIME (JP); MATSUSHITA ELE) 9 October 2003 (2003-10-09) * see p.4, 3rd and 4th par., see p13, table 1, claims * the whole document	1-5
Y	PATENT ABSTRACTS OF JAPAN vol. 0161, no. 38 (E-1186), 7 April 1992 (1992-04-07) & JP 03 297063 A (FUJII ELELCTROCHEM CO LTD), 27 December 1991 (1991-12-27) cited in the application abstract ----- -/--	1-5

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

3 February 2005

Date of mailing of the international search report

12.1.02.05

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Stellmach, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP2004/007585

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	PATENT ABSTRACTS OF JAPAN vol. 0124, no. 35 (E-683), 16 November 1988 (1988-11-16) & JP 63 168968 A (FUJI ELELCTROCHEM CO LTD), 12 July 1988 (1988-07-12) abstract -----	1-5
Y	US 4 806 441 A (BREZILLON JEAN L) 21 February 1989 (1989-02-21) * see col.2, l .26 - col..3, 1.33, claims * the whole document -----	1-5
Y	PATENT ABSTRACTS OF JAPAN vol. 0185, no. 04 (E-1608), 21 September 1994 (1994-09-21) & JP 06 176763 A (FUJI ELELCTROCHEM CO LTD), 24 June 1994 (1994-06-24) abstract -----	1-5
Y	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 02, 29 February 1996 (1996-02-29) & JP 07 272702 A (FUJI ELELCTROCHEM CO LTD), 20 October 1995 (1995-10-20) abstract -----	1-5
Y	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 01, 30 January 1998 (1998-01-30) & JP 09 237616 A (TOSHIBA BATTERY CO LTD), 9 September 1997 (1997-09-09) abstract -----	1-5
Y	US 3 891 463 A (KAROBATH ERNST ET AL) 24 June 1975 (1975-06-24) * see col.2, 28 - col 4, 1.3, claims * the whole document -----	1-5
Y	US 3 179 537 A (REILLY THOMAS A) 20 April 1965 (1965-04-20) * see fig..2,3, claims * the whole document -----	1-5

INTERNATIONAL SEARCH REPORT

on patent family members

International Application No

PCT/004/007585

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 03083962	A	09-10-2003	JP 2003297370 A EP 1490920 A2 WO 03083962 A2	17-10-2003 29-12-2004 09-10-2003
JP 03297063	A	27-12-1991	JP 2950574 B2	20-09-1999
JP 63168968	A	12-07-1988	JP 1972257 C JP 5061751 B	27-09-1995 07-09-1993
US 4806441	A	21-02-1989	FR 2607967 A1 DE 3778669 D1 EP 0273212 A1 ES 2031870 T3 JP 2070165 C JP 7097494 B JP 63150856 A	10-06-1988 04-06-1992 06-07-1988 01-01-1993 10-07-1996 18-10-1995 23-06-1988
JP 06176763	A	24-06-1994	NONE	
JP 07272702	A	20-10-1995	NONE	
JP 09237616	A	09-09-1997	NONE	
US 3891463	A	24-06-1975	DE 2262670 A1 AT 331322 B AT 1038273 A CH 559432 A5 DK 133799 B FR 2211764 A1 GB 1450814 A IN 140673 A1 JP 49089823 A PL 91165 B1 SE 407130 B ZA 7309663 A	11-07-1974 10-08-1976 15-11-1975 28-02-1975 19-07-1976 19-07-1974 29-09-1976 11-12-1976 28-08-1974 28-02-1977 12-03-1979 30-07-1975
US 3179537	A	20-04-1965	FR 1320643 A	08-03-1963

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.